

United States Patent [19]

Beck

[11] Patent Number: 4,670,530

[45] Date of Patent: Jun. 2, 1987

[54] PROCESS FOR MAKING CRUMB SILICONE MATERIAL

[75] Inventor: Earl W. Beck, Dublin, Calif.

[73] Assignee: Dow Corning Corporation, Midland, Mich.

[21] Appl. No.: 835,497

[22] Filed: Mar. 3, 1986

[51] Int. Cl.⁴ C08G 77/06

[52] U.S. Cl. 528/15; 528/31;
528/32; 524/781; 524/789; 525/478; 264/176.1;
264/331.11

[58] Field of Search 264/176 R, 331.11;
528/15, 31, 32; 525/478; 524/781, 789

[56] References Cited

U.S. PATENT DOCUMENTS

3,843,601 10/1974 Bruner 528/24
4,528,156 7/1985 Fukuda et al. 528/15

OTHER PUBLICATIONS

"Materials News from Dow Corning"/ Nov.-Dec. 1969, New Shock-Absorbing Bumper Turns 30-mph Crash into 5-mph Bump.—p. 3.

Primary Examiner—Melvyn I. Marquis

Attorney, Agent, or Firm—Roger H. Borrousch

[57]

ABSTRACT

Mixing under low shear vinyl-containing polyorganosiloxane, a silicon-bonded hydrogen polysiloxane and a platinum catalyst, and continue mixing produces a crumb which has an extrusion rate of at least 50 grams per minute through an orifice of 0.5 inch diameter under a pressure of 345 kilopascals and compression points of less than 1035 kilopascals. The crumb is useful in hydraulic applications.

31 Claims, No Drawings